

VULCANIZABLE FLUORORUBBER COMPOSITION

Patent number: JP5287152
Publication date: 1993-11-02
Inventor: TAKIZAWA MAKOTO; others: 01
Applicant: ASAHI CHEM IND CO LTD
Classification:
- international: C08L27/22; C08J3/24; C08K3/22
- european:
Application number: JP19920085519 19920407
Priority number(s):

Report a data error here

Abstract of JP5287152

PURPOSE: To provide the subject composition composed of a specified ratio of a specified fluororubber, a vulcanizing agent, a divalent metal oxide and a filler, excellent in heat resistance, oil resistance and compression set without requirement for secondary vulcanization and useful for an O-ring, a gasket, etc. of an automobile, etc.

CONSTITUTION: The objective composition is composed of (A) 100 pts.wt. fluororubber containing carbon-carbon double bonds in the polymer chain in an amount within a range of 0.005 to 2.0mol/kg (B) 0.1 to 20 pts.wt. vulcanizing agent such as an alkaline(earth metal-salt of bisphenol A, etc., (C) 0 to 30 pts.wt. divalent metal oxide such as magnesium oxide and (D) 0 to 100 pts.wt. filler such as carbon black.

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan